



FX-806 丙烯酸改性过氯乙烯防腐面漆

FX-806 Acrylic Modified Vinyl Perchloride Anticorrosive Finish

产品特性 Characteristics	漆膜干燥快 Fast drying. 具有优良的耐腐蚀和耐潮湿性能 Excellent resistance to corrosion and humidity. 有一定的耐化学品性能，亦有防延烧性 Offer chemical resistance, and prevent flame from spreading. 在-20℃仍可施工 Application can still be performed at -20 °C.	
产品用途 Uses	主要用于化工机械、设备、管道等金属、水泥构件的防腐涂装，可防止酸、碱及化学药品的腐蚀。 As anticorrosive coatings for metal or cement components surfaces of chemical machineries, equipment, pipelines to protect against corrosion of acid, alkali and chemical medicines.	
颜色 Color	各色 All colors	
施工条件 Equipment	无气喷涂 airless spray 喷嘴尺寸 nozzle orifice 压力 nozzle pressure 稀释比率 thinner ratio 适用于常规的喷涂、刷涂和辊涂	推荐 recommended 0.4~0.5mm 100~150kg/cm ² 0~5% by weight (重量比) May be applied by spray, brush, or roller.
稀释剂 Thinner	专用稀释剂 Special thinner	
混合比率 Mixing ratio	单组分 Single component	
涂装膜厚 Film thickness	干膜: 30μm/道 Wet film thickness: 30μm/coat	湿膜: 65μm/道 Wet film thickness: 65μm/coat
固体含量 Solid content	40%	40%



比重 Specific gravity	1.05 1.05
------------------------	--------------

涂覆率 Coverage rate	理论值 : 0.11 千克/平方米/30 μ m Theoretical: 0.11kg/m ² /30 μ m	0.105 L/平方米/30 μ m 0.105L/m ² /30 μ m
	实际值: 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.	

干燥时间 Drying time	温度(temperature) :	10 $^{\circ}$ C	20 $^{\circ}$ C	30 $^{\circ}$ C
	指触干燥(dry to touch) :	20mins	15mins	10mins
	实干(dry to handle):	3hrs	1.5hrs	1hrs

涂装间隔 Coating interval	Min. 最小	9hrs	7hrs	5hrs
	Max. 最大	—	—	—

储存期限 Shelf life	一年 12 months
--------------------	-----------------

包装规格 Packing	单组份包装: 20kg/桶 One component : 20kg/bucket
-----------------	--

表面处理 Surface preparation	底漆(中间漆)表面应清洁干燥, 无污物 The surface of primer or intermediate coat should be clean, dry and free from contamination. 用高压空气吹扫除去灰尘等污物 Remove any contaminants like dust by high pressure blower. 如果施工环境湿度大于 70%可加入适量的过氯乙烯防潮剂 Charge moderate amounts of Vinyl Perchloride Anti Blooming Agent if relative humidity of the application environment is greater than 70%.
-----------------------------	---

涂装配套 Coating system	适用底材: 涂刷过氯乙烯底漆的底材或参考我公司的配套。 Substrate: the surfaces coated with Vinyl Perchloride Primer, or refer to our system.
------------------------	--

安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical
------------------------------	--



attention.
保证良好的通风。
Assure well-ventilated working place.
小心火灾或爆炸。
Take precautions of the risks of fire or explosion.
现场遵守一切健康安全规定。
Observe all health and safety regulations on site

提醒注意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
