



## ACLH-304 沥青防污漆（船用）

## ACLH-304 Asphalt Antifouling Paint (for ships)

产品特性 Characteristics	有效防止藤壶、牡蛎、石灰虫、苔藓虫和藻类等海洋生物对船底的污损； Effectively prevent ship bottom from fouling with marine growths such as barnacle, oyster, lime insects, bryozoan and algae, etc. 保持船底光洁和航速不受影响，节省燃料，施工方便。 Remain a smooth ship bottom and do not affect the speed of ship so that this can save fuel. It also can provides ease of application.		
产品用途 Uses	适用于在海水中航行的中小船舶、码头设施和防止海洋生物污损船底的防污。 An antifouling coating for middle and small size ships sailing in seawater, and for dock facilities, and for ship bottoms to prevent from fouling of marine growths.		
颜色 Color	黑色、棕色 Black or brown		
施工条件 Application method	无气喷涂 Airless spray	推荐 Recommended	
	喷嘴尺寸 Nozzle tip	0.8~0.9mm	
	压力 Fluid pressure	100~150kg/cm <sup>2</sup>	
	稀释比率 Thinning ratio	0~5%	
	适用于无气喷涂、空气喷涂、刷涂及辊涂。 May be applied by airless spray, air spray, brush, or roller.		
稀释剂 Thinner	专用稀释剂 Special thinner		
混合比率 Mixing ratio	单组分 One-pack		
涂装膜厚 Film thickness	干膜: 50μm/道 Dry film thickness:50μm /coat	湿膜: 85μm/道 Wet film thickness:85μm /coat	
固体含量 Solid content	65%		
比重 Specific gravity	1.5		
涂覆率 Coverage rate	理论值 : 0.188kg/m <sup>2</sup> /50μm Theoretical:0.188kg/m <sup>2</sup> /50μm	0.118L/m <sup>2</sup> /50μm 0.118L/m <sup>2</sup> /50μm	
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.		
干燥时间	温度 (°C) Temperature (°C)	5	20      30



Drying time	指触干燥 (hrs)	8	3	20
	Dry to touch (hrs)			
	半硬干燥 (hrs)			
	Dry hard (hrs)			
涂装间隔	Min. 最小 (hrs)	24	16	12
Coating interval	Max. 最大 (day)	96	48	48
储存期限	一年			
Shelf life	12 months			
包装规格	25kg/桶			
Packing specification	25 kg/barrel			
表面处理	用适当的清洁剂和脱脂剂除去油脂；			
Surface preparation	Remove oil and grease with a suitable detergent or degreaser. 高压空气吹扫除去灰尘等污物； Remove dust and dirt by high-pressure air before paint application. 施工前确认表面清洁干燥。 Confirm the surface clean and dry.			
涂装配套	可与氯化橡胶类、乙烯类、环氧类、沥青类等油漆配套使用。			
Coating system	Compatible with chlorinated rubbers, ethylene, epoxy or asphalt paints.			
安全注意事项	任何油漆施工中均应保证提供以下措施：			
Safety Precautions	The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛，应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site.			
提醒注意	本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。			
Declaration	The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			