

**FX-803 氯磺化聚乙烯防腐面漆****FX-803 Chlorosulphonated Polyethylene Anticorrosive Finish**

产品特性 Characteristics	极好的防腐性能和耐候性 Excellent corrosion and weather resistance			
	同各类金属和水泥附着力良好 Good adhesion to all types of metal and cement			
	优良的耐水性 Excellent water resistance			
	良好的耐酸碱性和耐化学品性 Good acid, alkali and chemical resistance			
产品用途 Uses	主要用于石油化工设备、管线等受化工大气腐蚀的设施、亦可用于受酸、碱、盐腐蚀的贮槽和其他化工设备，也可用于水库、水槽、污水池等需要防水的设施。 Used for the facilities, such as petrochemical equipment and pipelines, where the coating is to be exposed to chemical atmosphere; and for storage tanks and other chemical equipment, where the coating is to be exposed to acid, alkali and salt; and also for the facilities like reservoirs, water channels and sewage sinks, which need water proofing.			
颜色 Color	各色 All colors			
施工条件 Equipment	无气喷涂 airless spray	喷嘴尺寸 nozzle orifice	压力 nozzle pressure	稀释比率 thinning ratio
				适用于常规的喷涂、刷涂和辊涂
	推荐 recommended	0.4~0.5mm	100~150kg/cm ²	0~5% by weight(重量比)
				May be applied by spray, brush, or roller.
稀释剂 Thinner	专用稀释剂 Special thinner			
混合比率 Mixing ratio	双组分: 主剂/固化剂=10/1 (重量比) Two component: base/curing agent=10/1 by weight			
混合使用期 Pot life	温度(temperature):	10°C	20°C	30°C
	混合使用期(pot life):	8hrs	6hrs	4hrs
涂装膜厚 Film thickness	干膜: 30µm/道	湿膜: 55µm/道		
	Dry film thickness: 30µm/coat	Wet film thickness: 55µm/coat		



固体含量 Solid content	41%			
比重 Specific gravity	1.16			
涂覆率 Coverage rate	理论值 : 0.11 千克/平方米/30 μ m Theoretical: 0.11kg/m ² /30 μ m	0.104L/平方米/30 μ m 0.104L/m ² /30 μ m		
	实际值:与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.			
干燥时间 Drying time	温度(temperature) :	10 $^{\circ}$ C	20 $^{\circ}$ C	30 $^{\circ}$ C
	指触干燥(dry to touch) :	40mins	30mins	20mins
	实干(dry to handle):	6hrs	5hrs	4hrs
涂装间隔 Coating interval	Min. 最小	6hrs	5hrs	4hrs
	Max. 最大	—	—	—
储存期限 Shelf life	一年 12 months			
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物 The surface of the primer should be clean, dry and free from contamination. 注意施工时与底漆的涂装间隔 Please take care of the coating interval.			
涂装配套 Coating system	适用下涂: 高氯化聚乙烯底漆、高氯化聚乙烯中间漆或参考我公司配套 Under coating : High Chlorinated Polyethylene Anticorrosive Primer, High Chlorinated Polyethylene Anticorrosive Intermediate, or refer to our system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。			



Assure well-ventilated working place.
小心火灾或爆炸。
Take precautions of the risks of fire or explosion.
现场遵守一切健康安全规定。
Observe all health and safety regulations on site

提 醒 注 意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
