

**FXH98-8 环氧胶泥****FXH98-8 Epoxy Resin Mortar**

产品特性 Characteristics	具有抗裂、抗冻、耐盐、耐碱、耐弱酸腐蚀性能 Resistance to crack, frost, salt, alkali and weak acid corrosion. 可与多种材料粘接性强 Strong adhesion to a variety of materials.
产品用途 Uses	主要用于水上建筑物过流面的抗冲磨损、抗气蚀、抗冻融保护，以及破坏后的修复。用于混凝土建筑物的缺陷修补及补加固处理。用于化工、石油、工厂、码头等混凝土或金属构件抗酸、碱、盐腐蚀的防护与修补。公路、桥梁、机场、跑道、车间等工程部位的抗磨损防护修补。用于耐酸砖的粘接。 For the flow surface of over-water buildings to have resistance to impact, air corrosion and freezing, as well as the repair of damage. I For the concrete buildings of defect repair and reinforcement. A coating with the resistance to acid, alkali and corrosive can protect and repair the concrete or metal components in chemical, petroleum, factories, docks,, etc. For components in roads, bridges, engineering airport, runway, workshop repair anti-wear protection. Used for bonding the acid-proof bricks.
颜色 Color	棕褐色粘稠液体，无硬结易搅动 Brown viscous liquid. No nod, stir easily.
施工条件 Application conditions	适用于常规的刷涂和辊涂 May be applied by spray, brush, or roller.
稀释剂 Thinner	FXH-4 环氧稀释剂 FXH-4 Epoxy Thinner
混合比率 Mixing ratio	双组分： 主剂/固化剂=2/1（重量比） Two components: base/curing agent=8/1 by weight
混合使用期 Pot life	温度： 25℃ Temperature 混合使用期 Pot life: 1hrs
涂装膜厚 Film thickness	干膜: 500μm/道 Dry film thickness:500μm/coat
固体含量 Solid content	100% 100%
比重 Specific gravity	1.85



涂覆率 Spreading rate	理论值 : 0.9 千克/平方米/500μm 0.49 L/平方米/500μm Theoretical: 0.21kg/m ² /100μm
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment, application method
干燥时间 Drying time	温度 25°C temperature 4hrs 指触干燥 dry to touch 72hrs 实干: dry to handle
涂装间隔 Coating interval	Min. 最小 —24 Max. 最大 —
储存期限 Shelf life	一年 12 months
包装规格 Package	双组份包装: 15kg 为一组, 组份一为 10kg, 组份二为 5kg 2K packaging: A kit 15kg contains Part A 10kg and Part B5kg.
表面处理 Surface preparation	1、基石应干燥, 坚实、无油污、无疏松、空鼓等现象。 The base shall be dry, solid, free of oil, the loose and the hollowing . 2、施工时应保持施工环境空气流通。 Keep good ventilation during application. 3、固化剂必须按比例配制, 注意适用期。 Add the curing agent according to the specified ratio, and pay attention to the pot life. 4、施工完后, 应及时用稀释剂清洗工具、器具保持干净。 After application, wash the tools immediately with thinner. Keep the tools clean.
涂装配套 Coating system	适用底材: 混凝土、钢铁 Substrate : concrete, steel 混凝土与混凝土、混凝土与钢铁、钢铁与钢铁之间的粘接 Bonding between concrete and concrete, concrete and steel, steel and steel 如有疑问请向津海公司咨询 If any question, please contact Jinhai.
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。



Observe all health and safety regulations on site

提 醒 注 意
Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
