



## FX-0210F 氟碳各色面漆

## FX-0210 Fluorocarbon Finishes

产品特性 Characteristics	极佳的防腐性能、极好的耐候性； Excellent corrosion and weather resistance 极好的耐油性和耐水性； Excellent oil and water resistance 极好的耐冲击和耐磨损性能； Excellent resistance to impact and abrasion 良好的施工性能。 Good workability			
产品用途 Uses	广泛用于桥梁、高速公路护栏、高档建筑、石油设备及储罐的防腐。 As anticorrosive finish widely for bridge, highway guardrail, high-grade building, petroleum equipment and storage tank			
颜色 Color	各色 All colors			
施工条件 Application methods	无气喷涂 airless spray 喷嘴尺寸 nozzle tip 压力 nozzle pressure 稀释比率 thinning ratio 适用于无气喷涂、空气喷涂、刷涂及辊涂 May be applied by spray, brush, or roller.	推荐 recommended 0.5~0.6mm 0.5~0.6mm 150kg/cm <sup>2</sup> 150kg/cm <sup>2</sup> 0~5% by weight (重量比) 0~5% (by weight)		
稀释剂 Thinner	氟碳稀释剂 Fluorocarbon thinner			
混合比率 Mixing ratio	双组分：主剂/固化剂=10/1 (重量比) Two component: base/curing agent=10/1 by weight			
混合使用期 Pot life	温度(°C): Temperature 混合使用期(hrs): Pot life	5°C 20°C 8 6	30°C 5	
涂装膜厚 Film thickness	干膜: 30μm/道 Dry film thickness: 30μm/coat			
固体含量 Solid content	60%			
比重 Specific gravity	1.15			
涂覆率 Spreading rate	理论值: 0.09kg/m <sup>2</sup> /30μm      0.078L/m <sup>2</sup> /30μm Theoretical: 0.09kg/m <sup>2</sup> /30μm      0.078L/m <sup>2</sup> /30μm  实际值: 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment and application method			
干燥时间 Drying time	温度(°C) Temperature (°C) 指触干燥(hrs) dry to touch (hrs)	5 20 1.5 0.7	30 0.5	



	实干: (hrs) Through dry (hrs)	6	4	3
涂装间隔 Coating interval	Min. 最小 (hrs) Min.(hrs) Max. 最大 (hrs) Max(hrs)	24 —	20 —	10 —
储存期限 Shelf life	一年 12 months			
包装规格 package	双组份包装: 22kg 为一组, 组份一为 20kg, 组份二为 2kg 2K packaging: A kit 22kg contains Part A 20kg and Part B 2kg.			
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物。 The surface of the primer must be clean , dry and free from contamination. 注意施工与底漆的涂装间隔。 Please pay attention to the coating interval.			
适用底材 Preferable substrate	氟碳底漆及多种底漆和中间漆配套或参考我公司的配套。 Compatible with fluorocarbon primer or other primers and intermediate coats, or refer to our coating system.			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。 In case of skin or eye contact, flush with large amount of water and immediately get medical attention. 保证良好的通风。 Assure well-ventilated working place. 小心火灾或爆炸。 Take precautions of the risks of fire or explosion. 现场遵守一切健康安全规定。 Observe all health and safety regulations on site			
提醒注意 Declaration	本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。 The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.			