

**TKEH-705 改性环氧压载舱防腐漆（灰色）****TKEH-705 Modified Epoxy Ballast Tank Anticorrosive Coating (Gray)**

产品特性 Characteristics	良好的耐油性、耐水性、油水交替腐蚀性 Good resistance to water and oil as well as favorable water and oil alternating corrosion resistance 极好的附着力 Excellent adhesion 气味小、毒性低 Low odor and toxicity 漆膜坚韧 Tough film			
产品用途 Uses	主要用于船舶压载舱涂装防腐，也可用于各种污水舱或污水管道等涂装防腐。 As anticorrosive coatings for ballast tanks, waste water tanks and sewage pipes, etc.			
颜色 Color	灰色 Gray			
施工条件 Application conditions	无气喷涂 airless spray	喷嘴尺寸 nozzle tip	压力 nozzle pressure	稀释比率 thinning ratio
	推荐 recommended	0.4~0.5mm 0.4~0.5mm	100~150kg/cm ² 100~150kg/cm ²	0~10% by weight（重量比） 0~10% by weight（重量比）
	适用于常规的喷涂、刷涂和辊涂 May be applied by spray, brush, or roller.			
稀释剂 Thinner	FXH-4 环氧稀释剂 FXH-4 Epoxy Thinner			
混合比率 Mixing ratio	双组分：主剂/固化剂=8/1（重量比） Two components: base/curing agent=8/1 by weight			
混合使用期 Pot life	温度： Temperature	10℃ 10℃	20℃ 20℃	30℃ 30℃
	混合使用期： Pot life	10hrs 10hrs	8hrs 8hrs	6hrs 6hrs
涂装膜厚 Film thickness	干膜：100μm/道 湿膜：185μm/道 Dry film thickness:100μm/coat Wet: film thickness:185μm/coat			
固体含量	75%			



Solid content	75%			
比重 Specific gravity	1.5			
涂覆率 Spreading rate	理论值 : 0.21 千克/平方米/100μm Theoretical: 0.21kg/m ² /100μm	0.148L/平方米/100μm 0.148L/m ² /100μm		
	实际值 : 与表面处理, 外界环境, 施工方法等多种因素有关。 Practical: varies depending on the surface treatment, environment, application methods			
干燥时间 Drying time	温度 temperature	10°C	20°C	30°C
	指触干燥 dry to touch	2hrs	1.5hrs	1hrs
	实干: dry to handle	14hrs	10hrs	8hrs
涂装间隔 Coating interval	Min. 最小 Min.	14hrs	10hrs	8hrs
	Max. 最大 Max.	—	—	—
储存期限 Shelf life	一年 12 months			
包装规格 package	双组份包装: 22.5kg 为一组, 组份一为 20kg, 组份二为 2.5kg 2K packaging: A kit 22.5kg contains Part A 20kg and Part B 2.5kg.			
表面处理 Surface preparation	用清水冲去盐分以及其它水溶性污物。 Remove salts and other water soluble contaminants with fresh water. 依照 SSPC-SP1 溶剂清洗标准除去油脂。 Remove oil in accordance with the solvent cleaning standard SSPC-SP1. 用喷砂方式除去铁锈、氧化皮和损坏的车间底漆达到 ISO Sa2.5 (SSPC-SP10)。 Remove rust and scale by sand blasting to ISO Sa 2.5 (SSPC-SP10) . 用高压空气吹扫除去灰尘等污物。 Remove the contaminants like dust with high pressure blower. 施工前确认表面清洁干燥。 Confirm the surface clean and dry before working.			
涂装配套 Coating system	适用底材: 裸钢 Substrate: bare steel 适用上涂: 参考我公司的配套 Top coat: refer to our coating system			
安全注意事项 Safety Precautions	任何油漆施工中均应保证提供以下措施: The following shall be guaranteed during any paint applications: 避免接触皮肤和眼睛。 Avoid skin and eye contact. 如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。			



In case of skin or eye contact, flush with large amount of water and immediately get medical attention.

保证良好的通风。

Assure well-ventilated working place.

小心火灾或爆炸。

Take precautions of the risks of fire or explosion.

现场遵守一切健康安全规定。

Observe all health and safety regulations on site

提醒注意

Declaration

本说明书所提供信息均为目前我方所掌握最全面正确的资料，鉴于产品使用条件非我方所能控制，此中信息不含担保，即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展，此中所有信息均以我方确认为准。

The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.
