

**FNUH-604 丙烯酸聚氨酯面漆 (各色) (船用或钢结构使用)****FXGH-604 Acrylic PU Topcoats (For ships or steel structures)**

产品特性 characteristics	优秀的耐候性 Excellent weather resistance 优秀的保光性和保色性 Excellent gloss and color retention 漆膜坚硬, 不粉化, 不泛黄 Hard film, free from chalking, non-yellowing 装饰性极佳, 干燥迅速 Excellent decorative effect, fast drying 优异的耐水性, 耐化学性, 耐油性, 耐冲击性, 耐磨性 Excellent resistance to water, chemicals and oil, as well as impact and abrasion resistance	
产品用途 Recommended use	适用于造船工业及沿海钢结构防腐涂装, 亦可用于集装箱货车以及大型钢铁设施、储罐外壁的防腐, 风力发电塔筒防腐等。 As anticorrosive coatings for shipbuilding, coastal steel structures, container trucks, large-scale iron and steel facilities, outside wall of tanks, and wind tower drums.	
颜色 Color	白色及各色 White and all colors	
施工条件 Application methods	无气喷涂 Airless spray 喷嘴尺寸 Nozzle orifice 压力 Nozzle pressure 稀释比率 Pimp ratio 适用于常规的喷涂、刷涂和辊涂	推荐 recommended 0.4~0.5mm 100~150kg/cm ² 0~3% by weight (重量比) May be applied by spray, brush, or roller.
稀释剂 Thinner	丙烯酸聚氨酯稀释剂 Polyurethane thinner	
混合比率 Mixing ratio	双组分: 主剂/固化剂=7/1 (重量比) Two component: Base/hardener=7/1 (by weight)	
混合使用期 Pot life	温度(temperature): 10℃ 20℃ 30℃ 混合使用期(pot life e): 6hrs 5hrs 3hrs	



涂装膜厚 Film thickness	干膜: 30 μ m/道 Dry film thickness: 30 μ m/coat	湿膜: 55 μ m/道 Wet film thickness: 55 μ m/coat
固体含量 Solid content	63%	63%
比重 Specific gravity	1.10-1.25	1.10-1.25
涂覆率 Coverage rate	理论值 : 0.10 千克/平方米/30 μ m Theoretical: 0.10 kg/m ² /30 μ m	0.09L/平方米/30 μ m 0.09L/m ² /30 μ m
	实际值: 与表面处理, 外界环境, 施工方法等多种因素有关。 Actual: depending on the surface treatment, environment and application methods.	
干燥时间 Drying time	温度(temperature) :	10 $^{\circ}$ C 20 $^{\circ}$ C 30 $^{\circ}$ C
	指触干燥(dry to touch) :	2hrs 1.5hrs 1hrs
	实干(dry to handle):	24hrs 12hrs 8hrs
涂装间隔 Coating interval	Min. 最小 Max. 最大	24hrs 12hrs 8hrs — — —
储存期限 Shelf life	一年 12 months	
包装规格 Packing	双组份包装: 22.8kg 为一组, 组份一为 20kg, 组份二为 2.8kg 2K packaging: A kit 22.8kg contains Part A 20kg and Part B 2.8kg.	
表面处理 Surface preparation	底漆表面应清洁干燥, 无污物 The primer surface should be clean, dry and free from contamination. 注意施工时与底漆的涂装间隔 Please take care of coating interval.	
涂装配套 Coating system	适用下涂: 多种底漆和中间漆配套或参考我公司的配套 Bottom coat : various primers and intermediate coats, or refer to my company's support	



安全注意事项 Safety Precautions	<p>任何油漆施工中均应保证提供以下措施:</p> <p>The following shall be guaranteed during any paint applications:</p> <p>避免接触皮肤和眼睛。</p> <p>Avoid skin and eye contact.</p> <p>如果油漆接触到皮肤或眼睛, 应用大量水冲洗并立即就医。</p> <p>In case of skin or eye contact, flush with large amount of water and immediately get medical attention.</p> <p>保证良好的通风。</p> <p>Assure well-ventilated working place.</p> <p>小心火灾或爆炸。</p> <p>Take precautions of the risks of fire or explosion.</p> <p>现场遵守一切健康安全规定。</p> <p>Observe all health and safety regulations on site</p>
提醒注意 Declaration	<p>本说明书所提供信息均为目前我方所掌握最全面正确的资料, 鉴于产品使用条件非我方所能控制, 此中信息不含担保, 即仅在选取产品上对买方负责。由于我公司产品及生产工艺的不断发展, 此中所有信息均以我方确认为准。</p> <p>The information given on this technical data sheet is correct to the best of our knowledge. In consideration of the application conditions of the product are beyond our control, so no guarantee is involved herein, namely, we are responsible for the buyers only in terms of their selecting a product. All data must be clarified from our company because of the constantly improvement of our product and its manufacturing process.</p>
